

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau




INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : H01M 2/04, B29C 45/00, H01M 2/08		A1	(11) International Publication Number: WO 99/65091
			(43) International Publication Date: 16 December 1999 (16.12.99)
(21) International Application Number: PCT/JP99/03126		(81) Designated States: AU, BR, CA, CN, ID, IN, KR, SG, US, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).	
(22) International Filing Date: 10 June 1999 (10.06.99)			
(30) Priority Data: 10/165118 12 June 1998 (12.06.98) JP		Published With international search report.	
(71) Applicant (for all designated States except US): MATSUSHITA ELECTRIC INDUSTRIAL CO., LTD. [JP/JP]; 1006, Oaza Kadoma, Kadoma-shi, Osaka 571-8501 (JP).			
(72) Inventors; and			
(75) Inventors/Applicants (for US only): YAMAMOTO, Kenji [JP/JP]; Matsushita Electric Industrial Co., Ltd., 1006, Oaza Kadoma, Kadoma-shi, Osaka 571-8501 (JP). KANEKO, Toshikazu [JP/JP]; Matsushita Electric Industrial Co., Ltd., 1006, Oaza Kadoma, Kadoma-shi, Osaka 571-8501 (JP). OKUBO, Takashi [JP/JP]; Matsushita Electric Industrial Co., Ltd., 1006, Oaza Kadoma, Kadoma-shi, Osaka 571-8501 (JP). SAEKI, Toshina [JP/JP]; Matsushita Electric Industrial Co., Ltd., 1006, Oaza Kadoma, Kadoma-shi, Osaka 571-8501 (JP).			
(74) Agent: ISHIHARA, Masaru; Fujiwara Building, 5th floor, 13-2, Kyomachi-bori 1-chome, Nishi-ku, Osaka-shi, Osaka 550-0003 (JP).			

(54) Title: SEALING STRUCTURE FOR AN ALKALI BATTERY

(57) Abstract

After a negative electrode current collector (10) has been inserted into an insertion hole (28a) therein, a resin sealing element (28) and negative electrode terminal plate (12) are successively inserted into an aperture (1a) of a battery casing (1), and the aperture rim of battery casing (1) is then bent inwards and crimped to seal aperture (1a) of battery casing (1). Sealing element (28) is accommodated within battery casing (1) in an arrangement facing negative electrode terminal plate (12), with resin injection gate (28c) corresponding to resin injection port (27a) of metal molds (22 - 24) during resin molding thereof positioned at the aperture end of battery casing (1).



FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

DESCRIPTION

SEALING STRUCTURE FOR AN ALKALI BATTERY

TECHNICAL FIELD

5 The present invention relates to an alkali battery, which employs a strongly alkaline liquid as electrolyte and of which aperture of the battery casing is hermetically sealed by a sealing unit chiefly consisting of resin.

10 BACKGROUND ART

 The typical construction of a cylindrical alkali battery, for example an alkali dry battery is as shown in Fig. 5, which shows a longitudinal cross-section thereof. Specifically, within a battery casing (positive electrode) 1 of cylindrical
15 shape having a head with a positive electrode terminal 8 projecting at its upper end face and an ornamental label 2 stuck on to its outer circumferential surface, there are inserted pellets of positive electrode mixture 3 which are molded in cylindrical shape and consist of manganese dioxide
20 and graphite added as conductive material. On the inside of this positive electrode mixture 3, there is poured in, separated by a separator 4, a gel-form zinc negative electrode 7 obtained by uniformly dispersing gelling agent and zinc alloy powder in an alkaline electrolyte in which is dissolved
25 potassium hydroxide.

 The aperture 1a of battery casing 1 is sealed as follows. In aperture 1a at the bottom of battery casing 1, a rod-shaped negative electrode current collector 10 made of brass is pressed into an insertion hole 9a and a resin sealing element
30 (gasket) 9 on to which is fitted an insulating washer 11 made of metal is fitted thereon. Negative electrode current collector 10 is then covered in electrically contacting fashion by a negative electrode terminal plate 12 contacting

its head 10a and a folded-back portion 9b formed on resin sealing element 9 is strongly pressed against negative electrode terminal plate 12 by bending and crimping inwards the edges of the bottom aperture of battery casing 1.

5 In the resin forming of sealing element 9, as shown in Fig. 6, a cavity 18 constituting a molding space for sealing element 9 is formed by mold assembly of lower metal mold 13, upper metal mold 14 and mandrel metal mold 17, and molten resin 20 passing through a resin passage 19a of annular
10 transverse cross-section of resin injection nozzle 19 is poured into this cavity 18 through a resin injection port 18a formed in annular shape by upper metal mold 14, resin injection nozzle 19 and mandrel metal mold 17. When the resin 20 that has been injected has solidified, the mold assembly
15 constituted by lower metal mold 13, upper metal mold 14 and mandrel metal mold 17 is broken open to obtain a sealing element 9 as described above.

Fig. 7 shows a sealing unit 21 assembled using a resin sealing element 9 formed by the molding steps described above.
20 Sealing unit 21 is assembled by pressing in and inserting negative electrode current collector 10 from the open end on the opposite side to resin injection gate 9c corresponding to resin injection port 18a when molding, into insertion hole 9a in sealing element 9. Insulating washer 11 is then mounted by
25 bringing it into contact with inner seat 9d and outer seat 9e, after which negative electrode terminal plate 12 is placed over insulating washer 11, by bringing its central portion into contact with and mounting it on head 10a of negative electrode current collector 10. In fitting this sealing unit
30 21 into aperture 1a of battery casing 1, when bending the bottom aperture 1a of battery casing 1 inwards, the folded-back portion 9b of resin sealing element 9 is strongly pushed on to negative electrode terminal plate 12 as shown by the

arrow.

Due to their use of a strongly alkaline liquid which is an alkaline aqueous solution of high concentration and large ion conductivity even at low temperature as electrolyte, such alkali batteries are able to withstand severe loading, have large capacity, and excellent low-temperature characteristics, and as a result are employed in equipment where power such as in particular motor drive power is needed. On the other hand, the strongly alkaline liquid that is used as electrolyte, due to its high permeability, is subject to the problem that leakage tends to occur due to creeping. Accordingly, sealing of aperture 1a of battery casing 1 is performed by forcing negative electrode current collector 10 into the insertion hole 9a, setting its external diameter to a value larger than the hole diameter of insertion hole 9a of resin sealing element 9, and bending and strongly crimping the aperture rim of battery casing 1.

However, in the case of the prior art sealing unit 21 shown in Fig. 7, small cracks appear in the resin injection gate 9c when negative electrode current collector 10 is inserted into insertion hole 9a of sealing element 9 by forcing it in from one end aperture at the opposite side to resin injection gate 9c on molding, whilst piercing and breaking flash 9f of resin injection gate 9c that closes the aperture at the other end, thereby widening this by pushing outwards. Since the resin injection gate 9c where these cracks start is arranged in contact with the electrolyte, electrolyte permeates into the cracks.

Also, in the case of high-temperature storage, heat cycle repetition, or prolonged storage at normal temperature, alkali batteries are subject to environmental stress cracking at locations subjected to excessive stress in a high-concentration alkaline aqueous solution (electrolyte)

atmosphere. In particular, resin injection gate 9c, due to the fact that resin deterioration tends to occur there because of the presence of residual stress on resin injection when molding, tends to constitute a starting point for the environmental stress cracks referred to above which are generated and develop continuously. For example, where 6,6-nylon is employed as the raw material of the sealing element 9, it is inferred that the high-concentration alkaline aqueous solution is selectively absorbed into non-crystalline portions that are present in the crystalline layer, and cracks are created in the gaps between non-crystalline portions in the spherical crystals due to the joint action of external stress and force of the absorbed alkaline aqueous solution tending to wet and spread.

As a result, due to electrolyte that has permeated into the small cracks generated in the resin injection gate 9c creeping up by the creeping phenomenon between the negative electrode current collector 10 and the hole circumferential surface of insertion hole 9a of sealing element 9, cracks are continuously generated and develop originating from the resin injection gate 9c which acquires residual stress during resin molding. In this way, electrolyte permeates as the cracks develop and eventually leaks to the outside.

The present invention has been devised in view of the above problems, its object being to provide an alkali battery wherein the generation of environmental stress cracks can be reliably prevented by a simple construction and whereby excellent resistance to leakage can be obtained.

DISCLOSURE OF THE INVENTION

According to the present invention, in order to achieve the above object, in an alkali battery wherein, after a negative electrode current collector has been inserted into an

insertion hole therein, a resin sealing element and negative electrode terminal plate are successively inserted into an aperture of a battery casing, and the aperture rim of said battery casing is then bent inwards and crimped to seal the aperture of said battery casing, said sealing element is accommodated within said battery casing in an arrangement facing said negative electrode terminal plate, with a resin injection gate corresponding to a resin injection port of a metal mold during resin molding thereof positioned at the aperture end of said battery casing.

With this alkali battery, since the resin injection gate corresponding to the resin injection port of the metal mold during resin molding of the sealing element is of a construction arranged at the aperture end of the battery casing and so not contacting the electrolyte, even if cracks are produced caused by residual stress during molding in the resin injection gate, electrolyte does not penetrate into these cracks, so the cracks do not develop to a sufficient degree to cause leakage of electrolyte. Excellent leakage-resistance performance can thereby be obtained.

Preferably in said invention the negative electrode current collector is forcibly inserted into an insertion hole passing through the central location of the sealing element to extend into the interior of the battery casing and is supported in a cantilevered manner, said insertion hole having a hole diameter smaller than the diameter of negative electrode current collector, and the sealing element has the resin injection gate at the aperture rim at the aperture end of said battery casing in said insertion hole.

In this way, since the metal mold for resin molding of the sealing element is of a construction in which a resin injection port is provided at the hole rim of the insertion hole in the middle of the cavity, resin molding of the sealing

element is easy. The negative electrode current collector is forced in from the aperture in the vicinity of the resin injection gate at the insertion hole of the sealing element, and although tiny cracks are produced in the resin injection gate which has residual stress on molding, these cracks are generated in a location on the opposite side to the electrolyte in the sealing element, thus, in contrast to the conventional alkali battery, they do not constitute a starting point for the development of environmental stress cracks due to permeation of electrolyte. Apart from this, leakage due to penetration of electrolyte by creeping between the sealing element and the negative electrode current collector can be reliably prevented since the negative electrode current collector is forced into an insertion hole of the sealing element whose hole diameter is set to be smaller than the diameter of the negative electrode current collector.

Also, according to the invention, the sealing element may be provided with the resin injection gate in its face at the aperture edge side of the battery casing in a side part offset from its center.

As a result, since the resin injection gate is positioned in a side part of the sealing element remote from the insertion hole, there is no possibility of cracks being produced therein when the negative electrode current collector is forced into the insertion hole; consequently the negative electrode current collector can be inserted by smoothly forcing it into the insertion hole.

Furthermore, a construction is desirable in which, in the invention, the aperture on the side adjacent the electrolyte in the insertion hole of the sealing element has a curved hole rim chamfered in radius shape. Consequently, when the negative electrode current collector is inserted by forcing it into the insertion hole of the sealing element, there is no

possibility of excessive stress being applied to the aperture rim of the insertion hole adjacent the electrolyte, so the generation of environmental stress cracks at locations of the sealing element adjacent the electrolyte can be reliably prevented; a further improvement in leakage resistance is thereby achieved.

BRIEF DESCRIPTION OF THE DRAWINGS

Fig. 1 is a cross-sectional view showing a molding step of a resin sealing element for an alkali battery according to an embodiment of the present invention;

Fig. 2 is a cross-sectional view showing a sealing unit of the above alkali battery;

Fig. 3 is a cross-sectional view showing a molding step of a resin sealing element of an alkali battery according to another embodiment of the present invention;

Fig. 4 is a cross-sectional view showing a sealing unit of the above alkali battery;

Fig. 5 is a longitudinal cross-sectional view showing the general construction of an alkali battery according to the present invention;

Fig. 6 is a cross-sectional view showing the molding step of a prior art alkali battery sealing element; and

Fig. 7 is a cross-sectional view showing a sealing unit of the above alkali battery.

BEST MODE FOR CARRYING OUT THE INVENTION

Preferred embodiments of the present invention are described below in detail with reference to the drawings. Fig. 1 is a cross-sectional view showing the step of molding a resin sealing element used in an alkali battery according to an embodiment of the present invention. In this Figure, a lower metal mold 22, upper metal mold 23 and mandrel metal

mold 24 are assembled, a cavity 27 constituting a molding space for the sealing element being formed within these. Molten resin 20 passing through resin passage 19a, which is annular in cross-sectional shape, of resin injection nozzle 19 is injected through resin injection port 27a formed in annular shape by upper metal mold 23, resin injection nozzle 19 and mandrel metal mold 24. After the injected resin 20 has hardened, the mold assembly constituted by lower metal mold 22, upper metal mold 23 and mandrel metal mold 24 is broken open, to obtain a sealing element 28 as shown in Fig. 2. In the molding of this sealing element 28, as is clear by comparison with Fig. 6 which shows a prior art molding step, the resin injection port 27a of resin 20 injected by resin injection nozzle 19 into cavity 27 is provided in a middle region of sealing element 28 that is to be molded outside of the battery which does not contact the electrolyte.

Fig. 2 shows a cross-sectional view of a sealing unit 29 constructed using a sealing element 28 obtained by the molding step described above. In this Figure, sealing element 28 is provided with a resin injection gate 28c at one end aperture hole rim of battery casing 1 on the side of aperture 1a in insertion hole 28a, and negative electrode current collector 10 is inserted by being forced in as shown by the arrow from the one end aperture adjacent resin injection gate 28c in this insertion hole 28a. After mounting on to sealing element 28 with insulating washer 11 abutting inner seat 28d and outer seat 28e, negative electrode terminal plate 12 is mounted in a condition with its middle part contacting head 10a of negative electrode current collector 10, overlying insulating washer 11, thereby constituting sealing unit 29.

When sealing unit 29 assembled in this way is fitted into aperture 1a of battery casing 1 as shown in Fig. 5, and the rim of the bottom aperture of battery casing 1 is then bent

inwards and crimped, the folded-back portion 28b of resin sealing element 28 is strongly pressed on to negative electrode terminal plate 12 as shown by the arrow, thereby sealing aperture 1a of battery casing 1 in liquid-tight manner.

5 When, in assembly of sealing unit 29, negative electrode current collector 10 is pressed into insertion hole 28a of sealing element 28 from one end aperture thereof corresponding to the resin injection gate 28c during molding, as a result of the insertion of negative electrode current collector 10 into
10 insertion hole 28a whilst piercing and breaking flash 28f created during molding that closes one end aperture such as to push it outwards, tiny cracks are formed in resin injection gate 28c that retains residual stress from when it was molded. However, these cracks are generated in locations in sealing
15 element 28 assembled in battery casing 1 which are on the opposite side to that of the electrolyte. Consequently, with an alkali battery wherein aperture 1a of battery casing 1 is closed in a sealed condition using the sealing unit 29 of Fig. 2, unlike the conventional alkali battery, the aforesaid
20 cracks do not provide a starting point for environment stress cracks induced by permeation of electrolyte. Furthermore, the resin injection gate 28c where cracks are liable to be produced because of the residual stress during molding is of a construction in which it is positioned on the opposite side to
25 the electrolyte in sealing element 28 and so does not contact the electrolyte. Even if cracks should be produced, such cracks cannot develop to the extent of permitting leakage of electrolyte by permeation of electrolyte as happens in a conventional battery; thus this battery has excellent leakage-
30 resistant performance.

Furthermore, since the other-end aperture on the side that contacts the electrolyte in the insertion hole 28a of sealing element 28 is constituted by a curved hole rim 28g

chamfered in radiused fashion, when negative electrode current collector 10 is inserted by forcing it into insertion hole 28a of sealing element 28, there is no possibility of excess stress being applied to the other-end aperture of insertion hole 28a that contacts the electrolyte. Leakage-resisting performance can therefore be further raised since occurrence of environmental stress cracks at locations of the sealing element 28 contacting the electrolyte can be reliably prevented.

Fig. 3 is a cross-sectional view showing the process of molding a resin sealing element used in an alkali battery according to a further embodiment of the present invention. In this Figure, lower metal mold 22 and mandrel metal mold 24 are the same as in the case of Fig. 1. Upper metal mold 30, together with lower metal mold 22 and mandrel metal mold 24, forms a cavity 27 of the same shape as in Fig. 1. However, in contrast to the cavity that is formed in annular shape in the middle position in Fig. 1, the resin injection port 27b of this cavity 27 in Fig. 3 is formed at a side location. Accompanying this, resin injection nozzle 31, which is of ordinary configuration, fits into upper metal mold 30 and is arranged such that resin 20 can be injected into cavity 27 through resin injection port 27b from this resin injection nozzle 31. It should be noted that resin injection ports 27b of cavity 27 could be formed at a plurality of side locations.

Fig. 4 shows a cross-sectional view of a sealing unit 33 constituted using a sealing element 32 obtained by the molding step described above. This sealing element 32 comprises an insertion hole 32a of the same shape as that of sealing element 28 of Fig. 2, a folded-back portion 32b, an inner seat 32d, an outer seat 32e and a curved hole rim 32f. The sole difference from sealing element 28 of Fig. 2 lies in that a resin injection gate 32c is provided on the inside face of the

side part. Sealing unit 33 is constituted by mounting negative electrode current collector 10, insulating washer 11 and negative electrode terminal plate 12 on this sealing element 32 in the same way as in Fig. 2.

5 With an alkali battery wherein aperture 1a of battery casing 1 is sealed in sealing condition using this sealing unit 33, when negative electrode current collector 10 is forced into insertion hole 32a of sealing element 32, resin injection gate 32c is remote from insertion hole 32a, so
10 insertion by forcing in negative electrode current collector 10 can be effected in a smooth fashion without production of cracks. Furthermore, since resin injection gate 32c where cracks are liable to be generated due to the presence of residual stress during molding, as in the embodiment described
15 above, is of a construction positioned at the face on the opposite side of sealing element 32 to the electrolyte, so that it does not contact the electrolyte, just as in the case of the alkali battery of the embodiment described above, excellent resistance to leakage can be obtained.

20 In order to ascertain the leakage-resistance performance of an alkali battery according to the above embodiments, the following tests were conducted. Resin sealing elements 28, 32 according to the embodiments were respectively molded by the molding steps of Fig. 1 and Fig. 3, using 6,6-nylon as
25 thermoplastic resin, and sealing units 29, 33 were assembled respectively constituted as shown in Fig. 2 and Fig. 4 using these sealing elements 28, 32. Two types of alkali battery according to the present invention were manufactured using these sealing units 29, 33. As a comparative example, a
30 conventional resin sealing element 9 was molded by the molding step of Fig. 6 likewise using 6,6-nylon and a sealing unit 21 was assembled constituted as shown in Fig. 7 using this sealing element 9. An alkali battery constituting a comparison

example was then manufactured using this sealing unit 21.

These alkali batteries were placed in a heat cycling atmosphere in which the temperature was varied with a heat cycle of 12 hours from 0° to 80° and their respective leakage-
5 resistance performances were evaluated. As a result, in the comparative example battery, axial cracks had developed to the extent of producing a defect by leakage of electrolyte, caused by entry of electrolyte into tiny cracks produced when the negative electrode current collector 10 in the resin injection
10 gate 9c was forced in. In contrast, in the alkali batteries of the embodiments of the present invention, since the starting point for crack generation by permeation of electrolyte was eliminated, defects due to leakage did not occur. In the above test, it was found that leakage due to axial cracks could be
15 effectively prevented if the ratio of the diameter of negative electrode current collector 10 with respect to the hole diameter of insertion hole 28a of sealing element 28 was set in the range 101% to 115%. It was also found that if this ratio was set to 100%, leakage occurred due to creeping of
20 electrolyte between the sealing element 28 and negative electrode current collector 10.

It should be noted that the same benefits as described above could be obtained by employing, apart from the 6,6-nylon described above, vinyl chloride, polypropylene, soft
25 polyethylene, or polyethylene terephthalate etc. as the material of sealing elements 28, 32. Furthermore, the same benefits as described above can be obtained by molding sealing elements 28, 32 by any of the methods: cold runner, semi-hot runner and hot runner.

30

INDUSTRIAL APPLICABILITY

As set forth above, in the alkali battery according to the present invention, a construction is adopted wherein the

resin injection gate corresponding to the resin injection port of the metal mold during resin molding of the sealing element is located at the aperture end of the battery casing so that it does not contact the electrolyte. Even if cracks are
5 produced due to residual stress on molding in the resin injection gate, such cracks are not in contact with electrolyte, and therefore they cannot develop to the extent of causing leakage of electrolyte; thus excellent leakage-resistance performance can be obtained.

CLAIMS

1. An alkali battery wherein, after a negative electrode current collector (10) has been inserted into an insertion hole (28a) therein, a resin sealing element (28) and negative electrode terminal plate (12) are successively inserted into an aperture (1a) of a battery casing (1), and the aperture rim of said battery casing (1) is then bent inwards and crimped to seal the aperture (1a) of said battery casing (1), characterized in that said sealing element (28) is accommodated within said battery casing (1) in an arrangement facing said negative electrode terminal plate (12), with a resin injection gate (28c) corresponding to a resin injection port (27a) of a metal mold during resin molding thereof positioned at the aperture end of said battery casing (1).

2. The alkali battery according to claim 1, wherein the negative electrode current collector (10) is forcibly inserted into the insertion hole (28a) passing through the central location of the sealing element (28) to extend into the interior of the battery casing (1) and is supported in a cantilevered manner, said insertion hole (28) having a hole diameter smaller than the diameter of the negative electrode current collector (10), and the sealing element (28) has the resin injection gate (28c) at the aperture rim at the aperture end of said battery casing (1) in said insertion hole (28a).

3. The alkali battery according to claim 1, wherein the sealing element (32) has the resin injection gate (32c) in its face at the aperture end side of the battery casing (1) in a side portion offset from the center.

4. The alkali battery according to claim 1, wherein the aperture edge on the side contacting the electrolyte in the insertion hole (28a) of the sealing element (28) is constituted by a curved hole rim (28g) chamfered in radiused shape.

Fig. 1




Fig. 2





Fig. 5

INTERNATIONAL SEARCH REPORT

A. CLASSIFICATION OF SUBJECT MATTER IPC 6 H01M2/04 B29C45/00 H01M2/08		International Application No PCT/JP 99/03126
According to International Patent Classification (IPC) or to both national classification and IPC		
B. FIELDS SEARCHED Minimum documentation searched (classification system followed by classification symbols) IPC 6 H01M B29C		
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched		
Electronic data base consulted during the international search (name of data base and, where practical, search terms used)		
C. DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 5 728 484 A (YAMAGUCHI MASAYOSHI ET AL) 17 March 1998 (1998-03-17) figures 10-18 column 3, line 58 - column 5, line 57 ---	1-4
A	PATENT ABSTRACTS OF JAPAN vol. 010, no. 306 (E-446), 17 October 1986 (1986-10-17) & JP 61 118961 A (MATSUSHITA ELECTRIC IND CO LTD), 6 June 1986 (1986-06-06) abstract ---	1-4
A	PATENT ABSTRACTS OF JAPAN vol. 009, no. 220 (E-341), 6 September 1985 (1985-09-06) & JP 60 081761 A (TOSHIBA DENCHI KK), 9 May 1985 (1985-05-09) abstract ---	1-4
-/--		
<div style="display: flex; justify-content: space-between;"> <input checked="" type="checkbox"/> Further documents are listed in the continuation of box C. <input checked="" type="checkbox"/> Patent family members are listed in annex. </div>		
<div style="display: flex;"> <div style="flex: 1;"> <p>* Special categories of cited documents :</p> <p>"A" document defining the general state of the art which is not considered to be of particular relevance</p> <p>"E" earlier document but published on or after the international filing date</p> <p>"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)</p> <p>"O" document referring to an oral disclosure, use, exhibition or other means</p> <p>"P" document published prior to the international filing date but later than the priority date claimed</p> </div> <div style="flex: 1;"> <p>"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention</p> <p>"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone</p> <p>"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.</p> <p>"&" document member of the same patent family</p> </div> </div>		
Date of the actual completion of the international search <div style="text-align: center; font-weight: bold;">26 August 1999</div>		Date of mailing of the international search report <div style="text-align: center; font-weight: bold;">03/09/1999</div>
Name and mailing address of the ISA European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Tx. 31 651 epo nl, Fax: (+31-70) 340-3016		Authorized officer <div style="text-align: center; font-weight: bold;">Engl, H</div>

INTERNATIONAL SEARCH REPORT

International Application No
PCT/JP 99/03126

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	PATENT ABSTRACTS OF JAPAN vol. 011, no. 033 (E-476), 30 January 1987 (1987-01-30) & JP 61 200665 A (MATSUSHITA ELECTRIC IND CO LTD), 5 September 1986 (1986-09-05) abstract ---	1-4
A	EP 0 538 039 A (EVEREADY BATTERY INC) 21 April 1993 (1993-04-21) , sentences 3-24 - column 2 page 7, line 9-27 -----	1-4

INTERNATIONAL SEARCH REPORT

Information on patent family members

I. International Application No

PCT/JP 99/03126

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5728484 A	17-03-1998	JP 9050794 A	18-02-1997
		CN 1148276 A	23-04-1997
		DE 19631329 A	06-02-1997
		FR 2737939 A	21-02-1997
JP 61118961 A	06-06-1986	NONE	
JP 60081761 A	09-05-1985	NONE	
JP 61200665 A	05-09-1986	NONE	
EP 0538039 A	21-04-1993	US 5227261 A	13-07-1993
		CA 2078892 A	16-04-1993
		DE 69226232 D	20-08-1998
		DE 69226232 T	21-01-1999
		JP 5205711 A	13-08-1993
		SG 44539 A	19-12-1997